

**DESCRIPTION**

PENESIL SILOX™ is a transparent, deep penetrating, non- staining, non-yellowing, non film-making, one component siloxane/silane water repellent, on façades and walls. PENESIL SILOX™ is a highly effective and long-lasting water repellent with excellent UV resistance. Easy to clean. Cures by reaction with ground and air moisture.

**RECOMMENDED FOR**

- ▶ Marble
- ▶ Decorative bricks
- ▶ Absorbent ceramic tiles
- ▶ Karystos slates
- ▶ Limestone
- ▶ Wood
- ▶ Concrete
- ▶ Plasters and porous screeds
- ▶ Concrete stone
- ▶ Natural stone
- ▶ Fiber reinforced cement

**ADVANTAGES**

- ▶ Simple application (roller, brush, spray)
- ▶ Gives a constant hydrophobic effect to the surface, without changing the color or the appearance of the surface
- ▶ No film formation. Allows the surface to breathe
- ▶ Non-yellowing
- ▶ No weathering effect. Retains its mechanical properties in a temperature range from -30 °C (-22 °F) to 90 °C (194 °F)
- ▶ Freezing resistant
- ▶ Ensures long-lasting effect
- ▶ Protects the surface from water intrusion, smog, acid rain and waterborne chloride ion migration. It reduces contaminant ingress and surface corrosion.
- ▶ Resistant to bacteria and fungus
- ▶ Reduces efflorescence

**TECHNICAL CHARACTERISTICS**

Characteristics	Test Result	Test Method
<i>Composition</i>	Siloxane/Silane, solvent based	
<i>Colour</i>	Clear	
<i>Resistance to water pressure</i>	No leak (1m water column, 24h)	DIN 1928, Test A
<i>Application Temperature</i>	5 °C to 35 °C (41 °F to 95 °F)	Conditions: 20 °C (68 °F) 50% RH
<i>Repaint time</i>	1-2 hours	
<i>Light pedestrian traffic time</i>	12 hours	
<i>Final curing time</i>	7 days	

All data are average values obtained under laboratory conditions. Impractical use, temperature, humidity and absorption of the substrate may influence the above given values.

**DIRECTIONS FOR USE**

**Surface Preparation:** The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the sealer. Maximum moisture content should not exceed 5%. Dirt, fats, oils, organic substances and dust need to be removed by mechanical grinding. Any loose surface pieces and dust need to be thoroughly removed. It is recommended to apply on a test area prior to application.

**NOTE:** Careful surface preparation is essential for optimum finish and durability. Do not wash surface with water.

**PENETRATING WATER REPELLENT**

**Application:** Apply PENESIL SILOX™ by using a roller or an airless spray gun. Apply a flood coat to ensure the deep penetrating and the full saturation, which is needed for effective water repellence. Fully saturate all mortar joints. Apply the second layer after 1-2 hours, while the first layer is still damp. For surfaces with frequent contact with water and especially on floor surfaces, we recommend applying three layers of the PENESIL SILOX™.

**NOTE:** Stir well before use.

**Coverage:** 3 - 4 m<sup>2</sup>/L per layer. Applied in two or three layers (consumption: 260 - 320 mL/m<sup>2</sup> per layer).

**SPECIAL CONSIDERATIONS**

The product is mainly applied to external absorbent surfaces as a water repellent protection. In case of indoor application, these areas should be well ventilated until the material is fully cured.

It is not recommended to be applied indoors in main living areas.

Careful compliance with the time margins is essential for an excellent result. Apply the product on a test area, to observe any deterioration or discoloration, prior to application.

For the best results, the temperature during application and cure should be between 5 °C (41 °F) and 35 °C (95 °F). Low temperatures retard cure, while high temperatures speed up curing. High humidity may affect the final finish.

Contact PENETRON HELLAS S.A. for further information, regarding your project.

**PACKAGING**

PENESIL SILOX™ is available in 1 L (0,23 gal), 5 L (1,14 gal) 13 L (2,95 gal) and 20 L (4,54 gal) containers.

**STORAGE / SHELF LIFE**

PENESIL SILOX™ has shelf life of maximum 18 months at 5 °C – 35 °C (41 °F – 95 °F), when stored in a dry enclosed area, away from direct solar radiation.

**SAFE HANDLING INFORMATION**

Flammable with a strong odor during application, but also until full curing. If contact with skin and eyes, flush areas with lots of water and seek medical advice. Protective gloves, mask and goggles should be worn. For further information please refer to Safety Data Sheet. PENETRON HELLAS S.A. has recently updated Safety Data Sheet on the safe use of PENETRON® products. Each Safety Data Sheet contains health and safety information for the protection of your employees and your customers. KEEP OUT OF REACH OF CHILDREND.

**CERTIFICATION**



PENETRON HELLAS S.A.  
50 Thrakomakedonon Av.,  
136 79 Acharnes, Greece  
22

1128-CPR-10.09.0479  
DOP NO: 14.026-49-01D160922-05  
EN 1504-2

PENESIL SILOX

Surface protection product - hydrophobic impregnation:

Protection against ingress [Method 1.1]

Moisture Control [Method 2.1]

Increasing Resistivity [Method 8.1]

Depth of penetration: Class I

Water absorption and resistance to alkali

Absorption ratio compared with the untreated

Specimen: < 7,5%

Absorption ratio after immersion in alkali

Solution: < 10%

Drying rate for hydrophobic

Impregnation: Class I: >30%

**WARRANTY - DISCLAIMER**

PENETRON HELLAS S.A. warrants that its products are manufactured under certified ISO Standard procedures, are of excellent quality and shall be free from material defects and contain all components in their proper proportion. Should any of the products be proven defective, the liability to PENETRON HELLAS S.A. shall be limited to replacement of the material proven to be defective, since the standard application procedures have been met and the suitability of the product for the particular application have been proven. PENETRON HELLAS S.A. makes no warranty as to merchantability of fitness for a particular purpose. User, after contacting the distributor of the product, shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith. While every care has been taken, the information provided in this product's data sheet make no part of any contract. All recommendations, technical data and test data contained in this product's data sheet are based upon the results of control laboratory tests or in actual field tests. However, PENETRON HELLAS S.A. makes no warranty of any kind, concerning this data. In any case, this data is given in good faith based in the PENETRON HELLAS S.A. experience, till the publication of this sheet. Due to variance in storage, handling and applications of the materials, PENETRON HELLAS S.A. accepts no liability for the results obtained. It is suggested that potential users try small applications to determine the suitability of each individual product for their specific requirements. The users should always refer to the most recent edition of the product's data sheet. PENETRON HELLAS S.A. may particularly differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information.

PENETRON HELLAS S.A.  
G.E.MH. No: 07278001000  
Athens Headquarters - Greece  
50 - 52, Thrakomakedonon Av.  
136 79 Acharnes, Greece  
T: +30 210 2448250  
F: +30 210 2476803  
info@penetron.gr, www.penetron.gr